

non-animal origin

rheological additive

for cosmetics and toiletries

GENERAL INFORMATION

BENTONE GEL IPM V is a specially prepared dispersion of a non-animal organically modified Hectorite in Isopropyl Myristate activated with Propylene Carbonate.

This grade is designed to impart rheological control and suspension to organic- and silicone-based cosmetics.

BENTONE GEL IPM V is also particularly useful in emulsions and can be used in "cold process" systems. It provides thermostable viscosity control of the emulsion's oil phase, improves application properties, enhances skin-feel by masking greasy or tacky components and imparts a pleasant residual silkiness to the skin. BENTONE GEL IPM V is an alternative to traditional polymer or cellulose-based thickeners for stabilising emulsions.

INGREDIENTS

INCI name:

Isopropyl Myristate, Stearalkonium Hectorite, Propylene Carbonate

CTFA name:

Isopropyl Myristate (and) Stearalkonium Hectorite (and) Propylene Carbonate

APPLICATIONS

- Antiperspirants
- Deodorant Sticks
- Hair preparations
- Eye Make-Up
- Creams & Lotions
- Sun Care Products
- Emulsions
- Lip Products

KEY PROPERTIES

BENTONE GEL IPM V rheological additive

Non-animal origin

Rheological control

- Predictable, reproducible and stable viscosity control
- Shear-thinning viscosity
- Excellent suspension of pigments and actives
- Controlled alignment of special-effect pigments
- Thermostable viscosity raises apparent melting point and ensures cost-efficient use of UV filters
- Emulsion stabilization [w/o and o/w]

Convenience

- Optimally pre-activated and dispersed organoclay
- Incorporates with medium-shear mixing
- Can be added at any convenient stage of manufacture
- Gives a high degree of formulating flexibility
- Provides highly reproducible results for multi-site production requirements

Acceptability

- Non-abrasive
- Provides smooth feel to skin
- Toxicologically safe ingredients

CHEMICAL AND PHYSICAL DATA

Color / Form Light tan paste

Viscosity 2500 - 4000

Brookfield Helipath,
TF spindle, Pa.s @
2.5 rpm

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2011, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

INCORPORATION

BENTONE GEL IPM V can be added at any convenient suitable stage during the manufacturing cycle. BENTONE GEL additive is a very high viscosity, shear-thinning product. To ensure good homogeneous mixing is achieved, care must be taken to overcome the large viscosity differential existing between the BENTONE GEL and the other lower viscosity components. Choice of mixing equipment and the configuration within the mixing vessels are critical factors in developing the optimum performance of the BENTONE GEL additives. The use of medium- to high-shear mixing equipment is recommended.

Batch Processing

Single Phase Systems

Always add the BENTONE GEL, under shear, to a portion of the organic component or solvent with which it is most compatible. Mix until homogeneous before adding the other ingredients.

Multi-Phase Systems e.g. emulsions

Treat as the single phase but always ensure the BENTONE GEL additive is thoroughly mixed in before the emulsification stage.

Continuous Processing

The BENTONE GEL should be added to the oil phase at any convenient point that meets the above guidelines for batch processing. In multi-manifold systems, a flowable pre-mix of the BENTONE GEL with a compatible oil or solvent should be made in a side pot.

Where only lower-shear mixing equipment is available, stir the BENTONE GEL alone and then slowly add the most compatible component by portions, always ensuring the mixture remains homogeneous at each stage.

LEVELS OF USE

The level of use of the BENTONE GEL will depend on the formulation. Suspension will be provided by 2.5-10.0% additions. In emulsions, thickening will occur in the oil phase only and emulsion viscosities will be influenced by 3-5% additions. Novel emulsification effects can be achieved,

giving light feel and lower viscosities. In some water-in-oil systems a reduction of surfactant may be achievable by the use of BENTONE GEL additive.

Higher levels of BENTONE GEL will have a greater viscosity influence and thermostable viscosity in single phase systems may be achieved by 10-25% additions.

COMPATIBILITY

BENTONE GEL additives can contribute greatly to a formulation's stability by improving the compatibility of other ingredients. Care should be taken to determine the compatibility of the BENTONE GEL additive with the oils, actives or surfactant ingredients within a formulation. The wide range of grades available allows selection of the optimal carrier and organoclay for each system.

TOXICITY

Care is taken to ensure that the ingredients used in BENTONE GEL additives are not known to be injurious to health in any way and have been toxicologically tested to ensure their safety. However, the BENTONE GEL additives have not been subjected to testing involving the use of animals within the last 10 years.

STORAGE TEMPERATURES

Store away from excessive heat. Keep from freezing. Store above 10°C.

SHELF LIFE

BENTONE GEL IPM V has a shelf life of 2 (two) years from date of manufacture.

SAFETY

Before using this product, please consult our MSDS

USA Head Office

Elementis Specialties, Inc.
P.O. Box 700
329 Wyckoffs Mill Road
Hightstown, NJ 08520 USA
Tel.: +1 609 443 2500
Fax: +1 609 443 2422

Europe

Elementis GmbH
Stolberger Strasse 370
50933 Cologne, Germany
Tel.: +49 221 2923 2000
Fax: +49 221 2923 2000

Asia

Elementis Specialties, Inc.
120 Jalan Kapar 27/89
40400 Shah Alam
Malaysia
Tel.: +60 3 5192 2887
Fax: +60 3 5192 3887

Japan

Elementis Japan KK
15-14 Minaminisemba 1-Chome
Chou-Ku, Osaka
542-0081 Japan
Tel.: +81 6 6267 6211
Fax: +81 6 6267 6215